

Granite Ceramic Adhesive Mortar

Product Description

Glazed porcelain, porcelain ceramic and granite ceramic adhesive mortar, high performance, cement based, with reduced sliding, extended holding time. (C2 TE)

Areas of Use

It is used for laying ceramic, glazed porcelain, porcelain ceramic and granite ceramic coatings on the wall and floor indoors and on the floor outdoors.

Application Surfaces

Interior wall:

- Cement-based plaster,
- Primed with gross concrete lining,
- Gypsum plaster and gypsum panel (Newkim Acrylic Primer applied)
- Old ceramic coating (Newkim Newsera applied)

Interior floor:

- Cement based screed,
- Concrete floor,
- Old ceramic coating (Newkim Newsera applied)

Outdoor floor;

- Cement based screed.
- Concrete floor.

Advantages

- Secure bonding in coatings such as oversized glazed porcelain, porcelain ceramics and granite ceramics.
- High performance in ceramic over ceramic applications.
 - Application possibility on plaster surfaces.



Preparation of the Surface

- The surface should be clean, dry, smooth and firm.
- Plasters thinner than 3 mm above the surface should be scraped and cleaned completely.
- Very porous surfaces should be wetted and the surface should remain moist until the water layer disappears.
- Any significant defects or holes in the surface should be repaired with a Newkim Thick Repair Mortar at least 24 hours prior to application of Granite Ceramic Adhesive Mortar.
- Regional repairs under 7 mm can be made using a Granite Ceramic Adhesive Mortar.

Preparation of Mortar

- Average 6-7 liters of water and 25 kg Granite Ceramic Adhesive Mortar should be mixed with a low speed mixer or trowel so that no lumps remain.
- Granite Ceramic Adhesive mortar should be mixed for 15-30 seconds before application after resting for 5 minutes.
- The mortar should be applied to the surface and its thickness should be adjusted with a threaded steel trowel.
- The tooth size of the trowel should be determined according to the size of the ceramic to be laid and the smoothness of the surface to be applied.

Application Limit

- It is not applied on metal surfaces.
- It is not applied on prefabricated and underfloor heated floors. (Newkim Flex Mortar Granite Adhesive Mortar should be used.)
- It is not applied on exterior facades.
 (Newkim Flex Mortar Granite Adhesive Mortar should be used.)

Application Requirements

Technical Data

- Ambient temperature is between +5 °C and +35 °C. It should not be applied on surfaces that are frozen, melting or that are in danger of frost within 24 hours.
- It should not be applied under direct sun, strong wind or on hot surfaces.
- During application, it should be paid attention that Newkim Granit Ceramic Adhesive Mortar does not form flm on the surface, if flm has formed, that part should be combed again.

Application Tools

Relative humidity environment of 55% (± 5 ° C) at 23 ° C (± 2 ° C). Bilgiler: 23°C

Hand mixer, trowel, rubber hammer, toothed steel trowel.

Warnings and Recomendations

- Certainly foreign materials should not be added to the mortar.
- Before application, the mortar should be thoroughly mixed until it reaches a homogeneous consistency.
- After application, all tools used should be washed with water before drying.

recilifical bata	(2 5 c) at 25 c (2 c). Single if, 25 c
Appearance	White and Gray
Powder Density	1.60 kg/ Lt. (±0.1)
Water Mixing Rate	6-7 lt. water / 25 kg. Powder
Resting Time	3-5 minutes
Pot Life	Approximately 2 hours
Working Time	Max. 20 minutes
Time Required For Joint Applic	ation 24 hours
Time To Open The Floor To Tra	ffic 24 hours (1 Week for heavy traffic)
Application Thickness	Between 3-10 mm (single or double side adhesive)
Slipping	≤0.5 mm (EN 1308)
High Initial Tensile Strength Fir	re Grade ≥1 N/mm² (EN 1348)
Fire Response Class	A1





