

## C 3000 APP-based (Plastomeric) Fibrocam Carrier Membrane



### Product Description

- Plastomeric waterproofing cover with APP (Atactic polypropylene) additive
- 60 gr / m<sup>2</sup> with fibrocam carrier
- Both sides covered with polyethylene film

### Areas of Use

- Water and steam insulation of wet places,
- Single or double floor insulation for retaining and basement walls,
- As a single or double layer in pressurized groundwater problems,
- As the first layer in secret creek insulation.

### Application Form

It is applied full, dotted or free with 10 cm at the joints and 15 cm at the end of the roll with the torch flame.

### Roll Length

10 mt.

### Storage & Protection

- The rolls are stocked vertically in a closed environment.
- They should not be exposed to ultraviolet rays and sudden changes in temperature.
- Period of time, they should be covered to protect them from the sun's rays.
- After application, piercing and cutting should not be done.
- Rolls are not placed on top of each other if they are to be stacked without pallets.
- In palletized stacking, it can be placed on top of each other with two rows of chipboard at the bottom.
- The terraces that are visited should be protected by floor covering.

### Technical

#### Specifications

	Test Name	Standart	Unit	Measurement Results
	Tensile Strength (Width - Length)	TS EN 12311-1	N/5 cm	200-300
	Breaking Elongation (Width -Length)	TS EN 12344-1	%	2-2
	Waterproof	TS prEN 1928		Waterproof
	Flow Resistance	TS 11758-1	°C	110
	Dimensional Stability	TS EN 1107-1	%	0.5
	Cold Shrinkage	TS EN 1109	°C	-5
	Tear Strength	TS EN 12310-1	N/5 cm	75
Dimensions	Thickness	TS EN 1849-1	mm	2
	Roll Length	TS EN 11758-1	m	10
	Roll Width	TS 11758-1	m	1
	Roll Weight		Kg. (min.)	34
	Bottom-Top Surface			PE/PE